

NOVARES TR 100

Reference-No. 142800

Description: Hydrocarbon resin; copolymerisation product from unsaturated aromatic C9-/C10-hydrocarbons with an unsaturated aliphatic component

Supply Form: solid (pastilles), 25 kg paper bags, big bags

Applications:

Adhesives and Sealants		
Tackifier for solvent-borne adhesives		
Rubber Industry		
Tackifier, especially for EPDM compounds		
Processing aid		
Modifier for chip and chunk resistance		
Coatings		
Modifier for alkyd coatings		

Specifications	Method	Value
Softening point (Ring & Ball)	acc. to ASTM D 3461	95-105 °C
Colour (Gardner) (50% in toluene)	ISO 4630	max. 15
Typical Properties *	Method	Value
Typical Colour	ISO 4630	< 10
Density at 20 °C	DIN 52 004	1,08-1,10 g/ml
Shelf Life		6 months
Naphthalene	AV-LAB-152	< 100 ppm
Iodine value	AV-LAB-128	> 120 gl2/100g

*) not specified, only for information;

Technical information, data and indications concerning function and application of the products are to be considered empirical values. Although the information is believed to be accurate, there is no warranty by Rain Carbon Germany GmbH. None of the recommendations becomes part of the contractual or warranted quality of the products. Due to the fact that the conditions of individual use are beyond Rain Carbon Germany GmbH control, Rain Carbon Germany GmbH disclaims all responsibility in connection with the use of the aforesaid material and does not warrant against any loss by reason of the use of the supplied products.

13.08.2020

Rain Carbon Germany GmbH

Varziner Strasse 49
D-47138 Duisburg

E-mail: resins@raincarbon.com
www.novares.de

phone: +49 / 203-4296-02
fax: +49 / 203-422551